

#3

IN THE UNITED STATES PATENT & TRADEMARK OFFICE

In re Patent Application of:

Michael Zimmer et al.

Serial No.: 09/641,595

Filed: August 18, 2000



Atty. Docket No. JFH-A12898US

Group Art Unit: Not Yet Assigned

Examiner: Not Yet Assigned

Title: METHOD FOR PRINTING ON A THERMOPLASTIC MATERIAL

\*\*\*\*\*

Jansson, Shupe, Bridge & Munger, Ltd.  
245 Main Street, Suite M  
Racine, Wisconsin 53403  
December 15, 2000

Hon. Commissioner of Patents & Trademarks  
Washington, D.C. 20231

Sir:

PRELIMINARY AMENDMENT

Before examining the above-referenced application, the Applicants request that the Examiner enter this Preliminary Amendment. This amendment is necessitated by the need to place the translated claims from the German application into proper format to comply with the rules of the U.S. Patent & Trademark Office. No new matter is added.

IN THE CLAIMS:

Please cancel claims 1-10 without prejudice and replace them with new claims 11-25 as follows:

CLAIMS

11. A method for printing on a thermoplastic material comprising the steps of:
  - applying by electrographic means a coloring agent having thermoplastic toner particles

to the thermoplastic material;

-bringing the thermoplastic material into a reactive state; and

-hardening the thermoplastic material thereby establishing a permanent bond between the coloring agent and the thermoplastic material.

12. The method of claim 11 wherein only a surface portion of the thermoplastic material is brought into a reactive state.

13. The method of claim 11 wherein the coloring agent is applied by an electrostatic means.

14. The method of claim 11 wherein the toner and material are brought to a malleable state.

15. The method of claim 11 wherein the toner and material are brought to a fluid state.

16. The method of claim 12 wherein the surface portion of the thermoplastic material is brought to a malleable state by means of thermal energy.

17. The method of claim 12 wherein the surface portion of the thermoplastic material is brought to a fluid state by means of thermal energy.

18. The method of claim 11 further comprising:

-processing the thermoplastic material in a heated molding machine;

-applying heat to at least the surface of the thermoplastic material to produce the reactive state;

-maintaining at least the surface of the thermoplastic material in the reactive state; and

-applying toner to the surface to be printed.

19. The method of claim 11 further comprising:

- heating the thermoplastic material in a molding machine;
- hardening the thermoplastic material;
- warming the hardened thermoplastic material in a warming device; and
- bringing the thermoplastic material into the reactive state at least in regions of its surface.

20. The method of claim 18 wherein the toner is brought to the reactive state by means of a warming device.

21. The method of claim 18 wherein:

- the surface of the material to be printed is in the reactive state;
- the toner is applied to the surface of the heated material to be printed; and
- the toner is brought to the reactive state by the material.

22. The method of claim 11 further comprising the steps of:

- processing the thermoplastic material in a heated molding machine;
- hardening the thermoplastic material;
- bringing the toner into the reactive state in a warming device;
- applying the toner to the surface of the material to be coated; and
- partially bringing the surface of the heated toner to the reactive state.

23. The method of claim 11 wherein:


- following the bonding of the coloring agent to the surface of the thermoplastic material;
- placing the thermoplastic material and the coloring agent in a cooling section; and
- bringing the thermoplastic material into a hardened state.

24. The method of claim 11 wherein the coloring agent is sunk into the surface of the

thermoplastic material to form a smooth surface structure.

25. The method of claim 11 wherein the thermoplastic toner particles are of the same thermoplastic material as the surface of the material to be coated.

Respectfully submitted,

  
David A. Frey  
Reg. No. 43,618


262/632-6900

262/632-6900

#### CERTIFICATE OF MAILING

I hereby certify that this correspondence is being deposited with the United States Postal Service as first class mail in an envelope addressed to Box Missing Parts, Assistant Commissioner for Patents, Washington, D.C. 20231 on 12-15-00

Date: 12-15-00

  
Sue Plagemann

#3

IN THE UNITED STATES PATENT & TRADEMARK OFFICE

In re Patent Application of:

Michael Zimmer et al.

Serial No.: 09/641,595

Filed: August 18, 2000



Atty. Docket No. JFH-A12898US

Group Art Unit: Not Yet Assigned

Examiner: Not Yet Assigned

Title: METHOD FOR PRINTING ON A THERMOPLASTIC MATERIAL

\*\*\*\*\*

Jansson, Shupe, Bridge & Munger, Ltd.  
245 Main Street, Suite M  
Racine, Wisconsin 53403  
December 15, 2000


Hon. Commissioner of Patents & Trademarks  
Washington, D.C. 20231

Sir:

STATEMENT CONCERNING FILING OF SUBSTITUTE  
SPECIFICATION PURSUANT TO 37 C.F.R. 1.125

In accordance with 37 C.F.R. § 1.125, applicants state that the attached substitute specification and abstract is filed in order to correct any faulty English that resulted from the translation of the originally-filed German specification and abstract and that such substitute specification and abstract contains no new matter.

Respectfully submitted,


  
David A. Frey  
Reg. No. 43,618

262/632-6900

CERTIFICATE OF MAILING

I hereby certify that this correspondence is being deposited with the United States Postal Service as first class mail in an envelope addressed to Box Missing Parts, Assistant Commissioner for Patents, Washington, D.C. 20231 on 12-15-00

Date: 12-15-00

  
Sue Plagemann

# METHOD FOR PRINTING ON A THERMOPLASTIC MATERIAL



## RELATED APPLICATION AND CLAIM OF PRIORITY

This application claims priority from German patent application DE 199 42  
5 O55.6-45 filed September 3, 1999.

## FIELD OF THE INVENTION

The invention pertains to a method for printing on a thermoplastic material,  
where a coloring agent is applied to the surface of the material and is subsequently  
10 caused to harden.

## BACKGROUND OF THE INVENTION

Various printing methods are known from the prior art, for example, silk  
screen, tampon printing or the flexoprint method. With these methods, solvent-  
15 containing dye is applied onto the thermoplastic material. The solvent is evaporated,  
so that the dye can harden. Some time after manufacture of the thermoplastic material,  
chemical reactions occur between the material surface and the formerly very difficult to  
scrape off dye, which adversely affect adhesion.

## 20 OBJECTS OF THE INVENTION

It is an object of the invention to create a method of the kind described above,  
wherein permanent coloration can be achieved on the material to be printed.

## SUMMARY OF THE INVENTION

25 The invention involves a method whereby as coloring agent, a toner featuring  
thermoplastic toner particles, is applied by electrographic or electrostatic means to the  
surface of the material, and that the toner and/or at least a portion of the surface of the  
material is brought into a reactive state in that the toner makes a permanent bond with  
the surface.

30 The thermoplastic toner particles enter into a permanent bond with the  
material, which later, in the hardened state, cannot be readily relaxed again. Thus,

permanent bonding of the coloring agent can be achieved. Because the coloring agent is applied in the form of a toner by electrographic or electrostatic means onto the material, a flexible printing process is possible, since even complicated printed patterns can be produced in very small lot sizes.

5           According to one preferred configuration variant of the invention, this method provides in particular for the surface of the material to be brought into a fluid or dough-like state by means of thermal energy.

One possible variant of the invention is characterized in that the thermoplastic material is processed in a molding machine under the influence of temperature, that the  
10           processed material is additionally heated at least in regions of its surface to produce the reactive state, or is kept in this reactive state under the influence of temperature, and that the toner is subsequently applied to the surface to be printed. Thus, in this case the printing process will directly follow the molding process.

According to another method of this invention, it is also provided that the  
15           thermoplastic material be processed in a molding machine under the influence of temperature, that subsequent to the molding process, the processed material be caused to harden (state Z1), and that the hardened material subsequently be sent to a warming device and brought into the reactive state at least in regions of its surface.

With regard to the two aforementioned methods, the toner can be brought to  
20           the reactive state by means of a warming device, or the toner can be brought into the reactive state by the thermal energy present in the material.

In addition, a process control is possible which is disconnected from the actual molding process. In this case, the invention provides that the thermoplastic material be processed in a molding machine under the influence of temperature, that subse-quent  
25           to the molding process, the processed material be caused to harden (state Z1), that the toner be brought into the reactive state in a warming device before application to the surface of the material to be coated, and that the surface of the heated toner be partially brought into the reactive state.

In order to ensure dependable hardening of the coloring agent, the invention  
30           also provides that subsequent to the coloration process, after the coloring agent has

bonded with the surface of the material, said material is brought into the hardened state together with the coloring agent in a cooling section.

As a result of the printing process, in order to cause little or no effect on the surface quality of the material, yet another method according to this invention provides that the coloring agent be sunken into the surface of the material to form a smooth surface structure. In this way, a homogeneous, smooth surface can be produced.

Preferably, the thermoplastic toner particles are of the same thermoplastic material as the material to be coated.

## 10 BRIEF DESCRIPTION OF THE DRAWINGS

The drawings illustrate preferred embodiments which include the above-noted characteristics and features of the invention. The invention will be readily understood from the descriptions and drawings. In the drawings:

FIGURE 1 is a schematic illustration of the process flow.

15

## DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

As is evident in the figure, a material 10 in the raw state is supplied to a molding machine 11. The molding machine, for example, can be an injection molding machine, an extruder or such. The molding machine 11 is associated with a warming device 14. By means of this warming device 14, the material 10 will be brought into the fluid or dough-like state. In conjunction with the molding process, printing of the entire material surface or a portion thereof will occur. In this case, a distinction is made in the process diagram between two states Z1 and Z2. According to state Z1, the material is caused to completely harden. The hardened material can then be transported or, for example, processed intermediately. Next, it is sent to a warming device 12. In this warming device 12, at least the surface of the material 10 to be printed is brought into a dough-like or fluid reactive state by means of thermal energy. By means of a printing device 13, a toner can be applied to the surface to be printed. The toner contains thermoplastic toner particles and dye pigments. If the toner is designed as a single component toner, then additional clarity control agents are also



present in the toner. Also, the use of a two-component toner is possible, to which a developer in the form of ferromagnetic particles has been added.

5 This toner will be applied electrographically or electrostatically to the surface of the material. Now, in this regard it is possible for the toner to be applied in its raw state directly to the surface of the material, or for the toner to be brought into the fluid or dough-like reactive state by means of a warming device 14. The toner can be added either before or after the warming device 12 in which the hardened material 10 is heated. If the toner is supplied to the material in the raw state, that is, not via the warming device 14, then conversion of the toner to the reactive state is caused either  
10 by the warming device 12, or directly by contact with the heated material 10. After the toner has been applied to the material 10 and has been brought into the reactive state, it will bond with the material 10 to form a permanent structure.

It is also possible that the hardened material 10 will not be supplied to the warming device 12, as is shown in the process outline. It is possible to apply to the  
15 material 10 a toner which was first brought to the reactive state by means of the warming device 14. Based on the temperature level of the toner, the surface of the material 10 will be locally melted, so that the coloring agent can bond with the surface; in particular, so it can sink into it.

It is also possible that the material 10 will be directly subjected to the dye  
20 treatment subsequent to the molding machine 11. In this case, at least the surface of the material 10 is still in the unhardened state Z2. If necessary, this state can be maintained with a supplemental heating device 17. Then, also, a toner can be applied to the surface of the material 10 with the printing device 13. The toner can either be applied to the surface in the raw state, or it can be pretreated with the warming device  
25 14.

After the coloring agent has been applied onto the material 10, the material will pass through a cooling section 15 where toner is caused to harden. After the printing process, the finished, printed workpiece 16 will be ready to use. Preferably, the thermoplastic toner particles of the toner consist of the same material as the material  
30 10, in order thus to obtain a consistent material composition. Preferably, the method

according to this invention will be used for the following materials: polyethylene, polypropylene, polystyrene, polycarbonate and ABS [acrylonitrile butadiene styrene].

Possible application examples for the new printing method are, for example, decoration of polycarbonate blends for household appliances, or printing of labels for compact disks, including bar codes, serial numbers or manufacturer data.

In addition, it is possible to provide polypropylene web plates with customer-related information (e.g., for the beverage industry). In the pharmaceutical industry, an individual batch code or identifier can be printed onto plastic packaging. To bring the thermoplastic material from the hardened state into the reactive state, the warming devices 12, 14, 17 can be designed as infrared emitters or as lasers which heat up only the near-surface layers of the material 10. Thus, deformation problems from thermal effects will be prevented.

While the principles of this invention have been described in connection with specific embodiments, it should be understood clearly that these descriptions are made only by way of example and are not intended to limit the scope of the invention.

	1990	1991	1992	1993	1994	1995	1996	1997	1998	1999	2000	2001	2002	2003	2004	2005	2006	2007	2008	2009	2010	2011	2012	2013	2014	2015	2016	2017	2018	2019	2020	2021	2022	2023	2024	2025	2026	2027	2028	2029	2030	2031	2032	2033	2034	2035	2036	2037	2038	2039	2040	2041	2042	2043	2044	2045	2046	2047	2048	2049	2050	2051	2052	2053	2054	2055	2056	2057	2058	2059	2060	2061	2062	2063	2064	2065	2066	2067	2068	2069	2070	2071	2072	2073	2074	2075	2076	2077	2078	2079	2080	2081	2082	2083	2084	2085	2086	2087	2088	2089	2090	2091	2092	2093	2094	2095	2096	2097	2098	2099	2100	2101	2102	2103	2104	2105	2106	2107	2108	2109	2110	2111	2112	2113	2114	2115	2116	2117	2118	2119	2120	2121	2122	2123	2124	2125	2126	2127	2128	2129	2130	2131	2132	2133	2134	2135	2136	2137	2138	2139	2140	2141	2142	2143	2144	2145	2146	2147	2148	2149	2150	2151	2152	2153	2154	2155	2156	2157	2158	2159	2160	2161	2162	2163	2164	2165	2166	2167	2168	2169	2170	2171	2172	2173	2174	2175	2176	2177	2178	2179	2180	2181	2182	2183	2184	2185	2186	2187	2188	2189	2190	2191	2192	2193	2194	2195	2196	2197	2198	2199	2200	2201	2202	2203	2204	2205	2206	2207	2208	2209	2210	2211	2212	2213	2214	2215	2216	2217	2218	2219	2220	2221	2222	2223	2224	2225	2226	2227	2228	2229	2230	2231	2232	2233	2234	2235	2236	2237	2238	2239	2240	2241	2242	2243	2244	2245	2246	2247	2248	2249	2250	2251	2252	2253	2254	2255	2256	2257	2258	2259	2260	2261	2262	2263	2264	2265	2266	2267	2268	2269	2270	2271	2272	2273	2274	2275	2276	2277	2278	2279	2280	2281	2282	2283	2284	2285	2286	2287	2288	2289	2290	2291	2292	2293	2294	2295	2296	2297	2298	2299	2300	2301	2302	2303	2304	2305	2306	2307	2308	2309	2310	2311	2312	2313	2314	2315	2316	2317	2318	2319	2320	2321	2322	2323	2324	2325	2326	2327	2328	2329	2330	2331	2332	2333	2334	2335	2336	2337	2338	2339	2340	2341	2342	2343	2344	2345	2346	2347	2348	2349	2350	2351	2352	2353	2354	2355	2356	2357	2358	2359	2360	2361	2362	2363	2364	2365	2366	2367	2368	2369	2370	2371	2372	2373	2374	2375	2376	2377	2378	2379	2380	2381	2382	2383	2384	2385	2386	2387	2388	2389	2390	2391	2392	2393	2394	2395	2396	2397	2398	2399	2400	2401	2402	2403	2404	2405	2406	2407	2408	2409	2410	2411	2412	2413	2414	2415	2416	2417	2418	2419	2420	2421	2422	2423	2424	2425	2426	2427	2428	2429	2430	2431	2432	2433	2434	2435	2436	2437	2438	2439	2440	2441	2442	2
--	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	---

5

10